

| Product name | Product group | Production location |
|--------------|---------------|---------------------|
| Ledbury      | L3            | Lanklaar            |

The raw materials are excavated in Weichsel loam layers, the local loam of Aeolian origin dating from the Ice Age. This löss mainly consists of a silt-like fraction, suited ideally for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.

|                                      | Colour  |                           |  |  |
|--------------------------------------|---|---------------------------|--|--|
| a shade of yellow to brown and black |   |                           |  |  |
| Format                               |   |                           |  |  |
| Moulding meti                        | Moulding method Hand form                                       |                           |  |  |
| DF: 215 x 102 x 65 mm                | Between batches the average size and color may slightly differ. |                           |  |  |
| Essential Characteristics - EN771-1  |   |                           |  |  |
| C E                                  |   | EN 771-1 - 0620-CPR-97884 |  |  |
| Dimensional tolerances               | T2  |                           |  |  |
| Range                                | R1  |                           |  |  |
| Active Soluble Salts                 | S2  |                           |  |  |
| Mean Compressive strength            | >= 20 N/mm²   | Tested to the bed face    |  |  |
| Normalized Compressive strength      | NPD   | Tested to the bed face    |  |  |
| Dimensional stability                | NPD   |                           |  |  |
| Bond Strength general                | 0,15 N/mm²  |                           |  |  |
| Bond Strength thin layer             | 0,30 N/mm <sup>2</sup>  |                           |  |  |
| Reaction to fire                     | A1  | Category                  |  |  |
| Water absorption                     | <= 17% m/md   |                           |  |  |
| Water vapour permeability            | 5/10  |                           |  |  |
| Net dry density                      | 1640 kg/m³ (D1)   |                           |  |  |
| Gross dry density                    | 1530 kg/m³ (D1)   |                           |  |  |
| Thermal conductivity Lambda 50/50    | <=0,55 W/m.K  |                           |  |  |
| Durability against freeze thaw       | F2  |                           |  |  |
| Dangerous substances                 | NL-BSB  | According to Annex ZA 3   |  |  |
| Other Characteristics                |   |                           |  |  |

| Other Characteristics                                |                              |                                      |  |  |
|--|------------------------------|--------------------------------------|--|--|
| Initial rate of water absorption - Non-coated Bricks | 1,5 - 4.0 kg/m².min<br>(IW3) | Value according EN771-1:2011 - 5.3.8 |  |  |
| Initial rate of water absorption - Coated bricks     | 0,5 - 1,5 kg/m².min<br>(IW2) | Value according EN771-1:2011 - 5.3.8 |  |  |
| Freeze/thaw resistance                               | NPD                          | В 27-009                             |  |  |
| Thermal conductivity Lambda 90/90                    | 0,60 W/m.K                   |                                      |  |  |
| Thermal conductivity Lambda Ui                       | 0,644 W/m.K                  |                                      |  |  |
| Thermal conductivity Lambda Ue                       | 1,27 W/m.K                   |                                      |  |  |











| Storage & handling   | Cutting  |  |
|--|--|--|
| - Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines | Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3). |  |

\*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.